

UBE Elastomer Co.Ltd.

Seavans North Bldg., 1-2-1, Shibaura, Minato-Ku, Tokyo
105-6791, Japan



TYPICAL PROPERTY SHEET

POLYBUTADIENE RUBBER
UBEPOL BR150B
PO No. :BR-25026

<u>TEST ITEMS</u>	<u>UNIT</u>	<u>DATA</u>	<u>TEST METHODS (UBE)</u>
Raw Polymer Mooney Viscosity	(ML1+4 100oC)	43	JIS K6300-1
Volatile Matter	(wt%)	0.7	JIS K6238-1
Ash	(wt%)	0.05	JIS K6228

(NOTE) DATA ; as per standard value