

## Stearic Acid

PRODUCT CODE	WILFARIN™ SA-1892	WILFARIN™ SA-1865	WILFARIN™ SA-1850	WILFARIN™ SA-1843	WILFARIN™ SA-1838	WILFARIN™ SA-1810	WILFARIN™ SA-1804
PRODUCT DESCRIPTION	Stearic Acid 92 %	Stearic Acid 65 %	Stearic Acid 50% Triple Pressed	Stearic Acid 43% Triple Pressed	Stearic Acid 38% Triple Pressed	Rubber Grade Stearic Acid	Rubber Grade Stearic Acid
<b>SPECIFICATION</b>							
Acid Value (mg KOH/g)	195-199	202-209	206-209	205-211	206-213	195 Min	195 Min
Sap Value (mg KOH/g)	196-200	203-210	207-210	206-211	207-214	196 Min	196 Min
Iodine Value (g I <sub>2</sub> /100g)	2 Max	0.5 Max	0.5 Max	0.5 Max	0.5 Max	4 Max	10 Max
Titre (°C)	66-70	58-63	55-57	54-57	54-56	52-57	52 Min
Colour (Lovibond 5¼" Cell), R/Y	0.5/2 Max	0.2/1.5 Max	0.3/1.3 Max	0.5/5 Max	0.3/3.0 Max	0.5/5 Max	5/50 Max
Moisture (%)	0.2 Max	0.1 Max	0.2 Max				
Unsap Matter (%)	1 Max	0.5 Max			1 Max		
Composition (%)							
C10							Variable
C12				1 Max	1 Max		
C14		2 Max	2 Max	2 Max	2 Max		
C15			0.5 Max				
C16	8 Max	30-33	45-49	49-58	57-65	75 Max	
C17			0.5 Max				
C18	92 Min	65-69	50-54	42-48	35-40	25 Min	
C18-1	2 Max	1 Max	0.5 Max	1 Max	2 Max		
C18-2	1 Max	0.5 Max					
C18-3							
C20	3 Max	1 Max	1 Max				
Others							
PRODUCT FORM	Liquid / Solid / Beads	Liquid / Solid / Beads	Liquid / Solid / Beads	Liquid / Solid / Beads	Liquid / Solid / Beads	Liquid / Solid / Beads	Liquid / Solid / Beads
PACKAGING	PB,PP,BB, ISO, Bulk	PB,PP,BB, ISO, Bulk	PB,PP,BB, ISO, Bulk	PB,PP,BB, ISO, Bulk	PB,PP,BB, ISO, Bulk	PB,PP,BB, ISO, Bulk	PB,PP,BB, ISO, Bulk
REMARKS	25 kgs Net / 50 kgs Net / bulk bags / ISO tank 20 mt / bulk						



For a healthy growing India

For more details and trade inquiries please contact [oleo.chemicals@adaniwilmar.in](mailto:oleo.chemicals@adaniwilmar.in)

ISO 14001:2004  
ISO 9001:2008

